


HIGH PERFORMANCE

OPTIMAL 1

Double-sided pattern for an excellent glare control

COLOUR 00020004 White Linen (Side A)



WIDTH(S)	250, 320 cm
DENSITY	1%
VISUAL COMFORT - WHITE LINEN (SIDE A)	
Glare control	1
View through	1
Privacy	2
Daylight	2
THERMAL COMFORT WITH GLAZING F	
Class interior	2
THERMAL AND VISUAL PROPERTIES	
Solar Reflectance Rs	57,5%
Solar Transmittance Ts	17,0%
Interior g-tot - Glazing F	0,343
Visual Transmittance Tv	0,148
Diffuse Visual Transmittance Tv _{n-dif}	0,136
Direct Visual Transmittance Tv _{n-n}	0,012

ABOUT THIS RANGE



Unlock augmented features with our cutting-edge fabrics, delivering high added value and best-in-class performance for glare control, temperature management or acoustical comfort.

OPTIMAL 1

- ✓ Optimal balance between visual and thermal performance thanks to its double-sided pattern
- ✓ Dark-coloured side for optimum glare control
- ✓ Reflective white side to allow maximum heat protection
- ✓ 2 other densities for tailored solar shading based on building orientation
- ✓ Extra wide width (320 cm)

TECHNICAL DATA

GENERAL FABRIC PROPERTIES

	Average value	Standard
Weighted composition	36% Fibreglass - 64% PVC	
Weaving pattern	Satin	
Width(s)	250, 320 cm	
Roll length (nominal)	Rolls of 33 lm	
Surface mass (weight)	450 g/m² ± 5%	ISO 2286-2
Thickness	0.61 mm ± 5%	ISO 2286-3
Colour fastness to artificial light (scale of 8)	≥ 7/8 (white not graded)	ISO 105 B02
Acoustic properties (αw)	0.3	ISO 10534-2

MECHANICAL PROPERTIES

	Average value	Standard
Breaking strength - Warp	>180 daN/5 cm	ISO 1421
Breaking strength - Weft	>140 daN/5 cm	ISO 1421
Elongation at break - Warp	<5%	ISO 1421
Elongation at break - Weft	<5%	ISO 1421
Tear strength - Warp	≥6 daN	ISO 4674-1 method 2
Tear strength - Weft	≥6 daN	ISO 4674-1 method 2

FIRE CERTIFICATES

		Standard
European Union - Spain	Class 1	EN 13773
France	M1	NF P 92-507
Germany	B1	DIN 4102-1
Italy	Classe Uno	UNI 9177
United States	FR	NFPA 701

THERMAL AND VISUAL PROPERTIES

Thermal properties

Solar Transmittance Ts (%)	17,0
Solar Reflectance Rs (%)	57,5
Solar Absorptance As (%)	25,5

Visual properties

Direct Visual Transmittance Tv _{n-n}	0,012
Diffuse Visual Transmittance Tv _{n-dif}	0,136
Diffuse Hemispherical Transmittance Tv _{dif-h}	0,130
Visual Transmittance Tv	0,148
Daylight	2
Glare control	1
Privacy	2
View through	1
UV Protection (Suv Class)	4

Thermal factors	Average value	Class
G _{tot} Glazing F	0,343	2
G _{tot} Glazing G	0,166	2
G _{tot} Glazing H	0,302	2

HEALTH, SAFETY AND OTHER PROPERTIES



Warranty



Printable



Fire retardant



Made in EU



Greenguard Gold