


DECORATIVE

RIYADH

Decorative double sided fabric

COLOUR 000000E8 Stone (Side A)



WIDTH(S)	250 cm
DENSITY	8%
VISUAL COMFORT - STONE (SIDE A)	
Glare control	0
View through	1
Privacy	1
Daylight	2
THERMAL COMFORT WITH GLAZING F	
Class interior	1
THERMAL AND VISUAL PROPERTIES	
Solar Reflectance Rs	29,1%
Solar Transmittance Ts	27,4%
Interior g-tot - Glazing F	0,490
Visual Transmittance Tv	0,273
Diffuse Visual Transmittance Tv _{n-dif}	0,203
Direct Visual Transmittance Tv _{n-n}	0,069

ABOUT THIS RANGE



Enhance your interior with our decorative fabrics featuring unique designs. Add personality and create an exclusive atmosphere that reflects your distinctive style. Choose from our collection to redefine your space.

RIYADH

- ✓ One-of-a-kind pattern woven with a jacquard technique
- ✓ Warm colours for a comforting atmosphere
- ✓ Keep vision toward the outside with dark colours
- ✓ Customizable: two distinctive side to choose your ideal match
- ✓ Contributes to a room's thermal and visual comfort

TECHNICAL DATA

GENERAL FABRIC PROPERTIES

	Average value	Standard
Weighted composition	28% Polyester - 72% PVC	
Weaving pattern	Jacquard	
Width(s)	250 cm	
Roll length (nominal)	Rolls of 27.4 lm	
Surface mass (weight)	464 g/m² ± 5%	ISO 2286-2
Thickness	1.07 mm ± 5%	ISO 2286-3

MECHANICAL PROPERTIES

	Average value	Standard
Breaking strength - Warp	>269 daN/5 cm	ISO 1421
Breaking strength - Weft	>152 daN/5 cm	ISO 1421
Elongation at break - Warp	<37%	ISO 1421
Elongation at break - Weft	<26%	ISO 1421
Tear strength - Warp	≥43 daN	ISO 4674-1 method 2
Tear strength - Weft	≥20 daN	ISO 4674-1 method 2

FIRE CERTIFICATES

		Standard
European Union - Spain	Class 1	EN 13773
France	M2	NF P 92-507
Italy	Classe Uno	UNI 9177
United States	FR	NFPA 701

THERMAL AND VISUAL PROPERTIES

Thermal properties

Solar Transmittance Ts (%)	27,4
Solar Reflectance Rs (%)	29,1
Solar Absorptance As (%)	43,5

Visual properties

Direct Visual Transmittance Tv _{n-n}	0,069
Diffuse Visual Transmittance Tv _{n-dif}	0,203
Diffuse Hemispherical Transmittance Tv _{dif-h}	0,232
Visual Transmittance Tv	0,273
Daylight	2
Glare control	0
Privacy	1
View through	1
UV Protection (Suv Class)	1

Thermal factors	Average value	Class
G _{tot} Glazing F	0,490	1
G _{tot} Glazing G	0,250	2
G _{tot} Glazing H	0,420	1

HEALTH, SAFETY AND OTHER PROPERTIES



Warranty



Printable



Fire retardant



Greenguard Gold