


EVOLUTION

ZILARIO 3

Metallised fabric to optimise glare control

COLOUR 00860086 Slate (Side A)



WIDTH(S)	240, 290 cm
DENSITY	2%
VISUAL COMFORT - SLATE (SIDE A)	
Glare control	3
View through	2
Privacy	2
Daylight	1
THERMAL COMFORT WITH GLAZING F	
Class interior	1
THERMAL AND VISUAL PROPERTIES	
Solar Reflectance Rs	36,9%
Solar Transmittance Ts	7,0%
Interior g-tot - Glazing F	0,477
Visual Transmittance Tv	0,040
Diffuse Visual Transmittance Tvn-dif	0,014
Direct Visual Transmittance Tvn-n	0,027

ABOUT THIS RANGE



Embrace the future sustainably with our next-generation fabrics. Engineered for innovation, designed for tomorrow's sustainable living.

ZILARIO 3

- ✓ Perfect for eco-friendly building initiatives like LEED and BREEAM
- ✓ Created from recycled PET bottles, free from PVC
- ✓ Effective glare control
- ✓ Due to its metallic side, the fabric offers superior solar reflection and outstanding visible transmission, regardless of the chosen colour
- ✓ Meeting diverse environmental standards

TECHNICAL DATA

GENERAL FABRIC PROPERTIES

	Average value	Standard
Weighted composition	100% recycled PET bottles	
Weaving pattern	Knitted	
Width(s)	240, 290 cm	
Roll length (nominal)	Rolls of 30 lm	
Surface mass (weight)	226 g/m ² ± 5%	ISO 2286-2
Thickness	0.52 mm ± 5%	ISO 2286-3
Colour fastness to artificial light (scale of 8)	≥ 2/8 (white not graded)	ISO 105 B02
Acoustic properties (αw)	0.34	ISO 10534-2

MECHANICAL PROPERTIES

	Average value	Standard
Breaking strength - Warp	>153 daN/5 cm	ISO 1421
Breaking strength - Weft	>127 daN/5 cm	ISO 1421
Elongation at break - Warp	<33%	ISO 1421
Elongation at break - Weft	<34%	ISO 1421
Tear strength - Warp	≥22 daN	ISO 4674-1 method 2
Tear strength - Weft	≥20 daN	ISO 4674-1 method 2

FIRE CERTIFICATES

		Standard
Euroclass	B-s1,d0	EN 13501-1
European Union - Spain	Class 1	EN 13773
France	M1	NF P 92-507
Germany	B1	DIN 4102-1
Italy	Classe Uno	UNI 9177
United Kingdom	Type C	BS 5867 part 2
United States	FR	NFPA 701

THERMAL AND VISUAL PROPERTIES

Thermal properties

Solar Transmittance Ts (%)	7,0
Solar Reflectance Rs (%)	36,9
Solar Absorptance As (%)	56,1

Visual properties

Direct Visual Transmittance Tv _{n-n}	0,027
Diffuse Visual Transmittance Tv _{n-dif}	0,014
Diffuse Hemispherical Transmittance Tv _{dif-h}	0,032
Visual Transmittance Tv	0,040
Daylight	1
Glare control	3
Privacy	2
View through	2

UV Protection (Suv Class)	3	
Thermal factors	Average value	Class
Gtot Glazing F	0,477	1
Gtot Glazing G	0,268	2
Gtot Glazing H	0,416	1

HEALTH, SAFETY AND OTHER PROPERTIES



Warranty



Printable



PVC free



Fire retardant



Made in EU



Greenguard Gold



Cradle to Cradle Bronze



Oeko-Tex